
TITANIUM OXIDE(V), Ti₃O₅

CAS	12065-65-5				
Melting Point (°C)	1700				
Evaporation Temperature (°C)	2200				
Density (g/cm³)	4.57				
Refractive Index	2.3				
Transmission Range (µm)	0.4~12				
Evaporation Source	E				
Application Interference Film, Multilayers Coating					
DOT Class	NR				
Part No.	Production Description	Size mm	Purity %	Price, USD	
				100g	500g
T-601	Ti3O5 Highly	ø8~10×5~7	99.9	220	580

Sintered Dark Blue Tablet					
T-602	Ti3O5 Highly Sintered Black Granule	3~6	99.9	250	630
T-603	Ti3O5p Premelted Granules	3~10	99.99	280	660
T-604	Ti3O5 Sparking Crystal Granules	1~3	99.99	300	680