



US 20140248742A1

(19) **United States**

(12) **Patent Application Publication**
Gonzalez et al.

(10) **Pub. No.: US 2014/0248742 A1**

(43) **Pub. Date: Sep. 4, 2014**

(54) **MULTI-CHIP PACKAGE HAVING A SUBSTRATE WITH A PLURALITY OF VERTICALLY EMBEDDED DIE AND A PROCESS OF FORMING THE SAME**

Publication Classification

(51) **Int. Cl.**
H01L 25/00 (2006.01)
(52) **U.S. Cl.**
CPC *H01L 25/50* (2013.01)
USPC **438/107**

(71) Applicants: **Javier Soto Gonzalez**, Chandler, AZ (US); **Houssam Jomaa**, Phoenix, AZ (US)

(72) Inventors: **Javier Soto Gonzalez**, Chandler, AZ (US); **Houssam Jomaa**, Phoenix, AZ (US)

(21) Appl. No.: **14/279,165**


(22) Filed: **May 15, 2014**

Related U.S. Application Data

(62) Division of application No. 12/976,903, filed on Dec. 22, 2010, now Pat. No. 8,736,065.

(57) **ABSTRACT**

An apparatus includes a substrate having a land side having a plurality of contact pads and a die side opposite the land side. The apparatus includes a first die and a second die wherein the first die and second die are embedded within the substrate such that the second die is located between the first die and the land side of the substrate.






FIG. 1B




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 2H




FIG. 2I




FIG. 2J




FIG. 2K




FIG. 2L




FIG. 3

**MULTI-CHIP PACKAGE HAVING A
SUBSTRATE WITH A PLURALITY OF
VERTICALLY EMBEDDED DIE AND A
PROCESS OF FORMING THE SAME**

[0001] This is a Divisional application of Ser. No.: 12/976, 903 filed Dec. 22, 2010, which is presently pending.

BACKGROUND

[0002] 1. Field

[0003] Disclosed embodiments relate to semiconductor microelectronic packages and methods of formation.

[0004] 2. Discussion of Related Art

[0005] Today's consumer electronics market frequently demands complex functions requiring very intricate circuitry. Scaling to smaller and smaller fundamental building blocks, e.g. transistors, has enabled the incorporation of even more intricate circuitry on a single die with each progressive generation. On the other hand, although scaling is typically viewed as a reduction in size, multiples of packaged die are increasingly coupled together for advanced functionality and horse-power in a computing system. Also, the size of a particular semiconductor package may in fact be increased in order to include multiple die within a single semiconductor package.

[0006] However, structural issues may arise when attempting to couple multiples of packaged die. For example, the effect of differences in the coefficients of thermal expansion (CTE) between components used in the semiconductor packages can lead to detrimental defects when adding packaged die together. Similarly, the effect of differences in the coefficients of thermal expansion (CTE) between components used within a single semiconductor package can lead to detrimental defects as a result of performing a semiconductor die packaging process for more than one die within the single package.

[0007] Semiconductor packages are used for protecting an integrated circuit (IC) chip or die, and also to provide the die with an electrical interface to external circuitry. With the increasing demand for smaller electronic devices, semiconductor packages are designed to be even more compact and must support larger circuit density. For example, some semiconductor packages now use a coreless substrate, which does not include the thick resin core layer commonly found in conventional substrates. Furthermore, the demand for higher performance devices results in a need for an improved semiconductor package that enables mixed technology die stacking or provide package stacking capability while maintaining a thin packaging profile and low overall warpage to be compatible with subsequent assembly process.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] In order to understand the manner in which embodiments are obtained, a more particular description of various embodiments briefly described below will be rendered by reference to the appended drawings. These drawings depict embodiments that are not necessarily drawn to scale and are not to be considered to be limited in scope. Some embodiments will be described and explained with additional specificity and detail through the use of the accompanying drawings in which:

[0009] FIGS. 1A and 1B illustrate a multi-chip package (MCP) having a plurality of die embedded within a substrate

and vertically arranged therein in accordance with an embodiment of the present invention.

[0010] FIGS. 2A-2L illustrate a method of forming a multi-chip package (MCP) having a plurality of die embedded within a substrate and vertically arranged therein in accordance with an embodiment of the present invention.

[0011] FIG. 3 shows a computer system according to an embodiment of the invention.

[0012] FIG. 4 illustrates a multichip package having more than two die embedded within a substrate and vertically arranged therein in accordance with an embodiment of the present invention.

[0013] FIG. 5 illustrates a multichip package having more than two die embedded within a substrate and vertically arranged therein in accordance with another embodiment of the present invention.

DETAILED DESCRIPTION

[0014] A multi-chip package (MCP) having a plurality of vertically embedded die and its method of manufacture are described. Reference will now be made to drawings wherein like structures may be provided with like suffix reference designations. In order to show the structure of various embodiments more clearly, the drawings included herein are diagrammatic representations of the integrated circuit structures. Thus, the actual appearance of the fabricated integrated circuit structures, for example in a photomicrograph, may appear different while still incorporating the claim structure of the illustrated embodiments. Moreover, the drawings may show only structures useful to understand the illustrated embodiments. Additional structures known in the art may not have been included to maintain the clarity of the drawings. Additionally, in the present description numerous specific details have been set forth in order to provide a thorough understanding of embodiments of the present invention. In other instances, well known semiconductor processing and packaging techniques have not been set forth in specific detail in order to not unnecessarily obscure embodiments of the present invention.

[0015] Embodiments of the present invention include a multi-chip package having a substrate with a plurality of vertically arranged die embedded therein. The substrate includes a land side and a die side. A first die and a second die are embedded within the substrate such that the second die is between the first die and the land side of the substrate. The package substrate includes a plurality of routing layers, insulating layers, and vias for creating an interconnection structure within the substrate which provides electrical connection between the first die and the second die. In an embodiment of the present invention, at least one routing layer is located between the first die and the second die. The multi-chip package having a substrate with vertically arranged and embedded die therein in accordance with embodiments of the present invention may be formed with a bumpless build-up layer (BBUL) process. In an embodiment of the present invention, the first die is attached to a temporary carrier and an insulating and routing layer are built over and around the first die embedding the first die therein. A second die is then attached to one of the insulating layers and additional insulating layers and routing layers built up and around the second die thereby embedding the second die within the substrate as well. In this way, both the first and second dies are embedded with the substrate and electrical interconnections are formed within the substrate (substrate routing) that electrically couple the

first and second die. The carrier may subsequently be removed to create a coreless substrate.

[0016] Embodiments of the present invention enable the formation of the multi-chip package with a thin package configuration and a small footprint thereby saving valuable space on device motherboards. Additionally, embodiments of the present invention enable the electrical connection of two die without the use of package-on-package (POP) technology which requires surface mount technology (SMT) which can be susceptible to reliability issues due to substrate warpage. Additionally, in embodiments of the present invention, a low temperature bumpless build-up layer (BBUL) process is used to form the substrate so as to reduce or eliminate the effects of coefficient of thermal expansion (CTE) mismatch between the embedded dies and the substrate thereby enabling the fabrication of a very planar multi-chip package.

[0017] FIG. 1A is an illustration of a cross-sectional view of a semiconductor package 100 having a substrate 102 with a plurality of vertically arranged die embedded therein. In an embodiment of the present invention substrate 102 is a coreless substrate. Substrate 102 has a die side 120 and a land side 122 opposite the die side. Package 100 contains a first die 104 and a second die 106. The first die 104 has an active surface 108 and a back surface 110 opposite the active surface 108. Similarly, second die 106 has an active surface 112 and a back surface 114 opposite the active surface 112. First die and second die may be formed from any well know semiconductor material, such as but not limited to silicon (Si), silicon germanium (SiGe), germanium (Ge) as well as any III-V semiconductor, such as gallium arsenide (GaAs) and indium antimonide (InSb). The active surfaces 108 and 112 include a plurality of semiconductor devices, such as but not limited to transistors, capacitors and resistors interconnected together by a die interconnection structure into functional circuits to thereby form an integrated circuit. As is well know in the art, the die interconnect structure may include any number of metallization layers, such as M1-M11, whose number and thicknesses may vary depending upon a given application utility. The first level of metallization (M1) makes contact with the semiconductor devices of active surface while the last level of metallization (e.g. M11) includes electrical contacts for making connection to the outside world. First die 104 is shown having electrical contacts 116 and second die 106 is shown having electrical contacts 118. In an embodiment of the present invention, active surface 108 of first die 104 and active surface 112 of second die 106 face towards or face in the same direction as a plurality of external conductive contacts 140 formed on substrate 102 as illustrated in FIG. 1A. That is, first die 104 and second die 106 are arranged in a “face down” configuration in substrate 102.

[0018] First die 104 has a first footprint or surface area 105 and second die 106 has a second footprint or surface area 107. In an embodiment of the present invention, first die 104 has a larger footprint than second die 106. Second die 106 is embedded within substrate 102 and is positioned between first die 104 and land side 122 of substrate 102. In this way, first die 104 and second die 106 are vertically arranged within substrate 102. In an embodiment of the present invention, at least a portion of footprint 107 of second die 106 lies within the footprint 105 of first die 104. In an embodiment, as illustrated in FIG. 1A, the entire footprint 107 of second die 106 lies within the footprint 105 of first die 104. In an embodiment of the present invention, first die 104 is a memory device, such as but not limited to a static random access memory (SRAM),

a dynamic access memory (DRAM), a nonvolatile memory (NVM) and second die 106 is a logic device, such as but not limited to a microprocessor and a digital signal processor.

[0019] Land side 122 includes a plurality of conductive contact pads and/or routing traces to which a plurality of external conductive contacts 140 are connected. External conductive contacts 140 provide electrical connection of package 100 to other devices. Substrate 102 includes a plurality of routing layers, insulating layer and vias which together create a substrate interconnection structure. The substrate interconnection structure provides electrical connection between the first die 104 and second die 106 as well as providing electrical connection of the first and second die to external electrical contacts 140 formed on land side 122.

[0020] The substrate interconnection structure provides direct electrical connections of first die 104 to second die 106 so that signals may be directly passed between first die and second die. The substrate interconnection structure may also include electrical connections between second die 106 and external conductive contacts 140. In some embodiments of the present invention, the substrate interconnection structure also provides an electrical connection between the first die 104 and external electrical contacts 140. In other embodiments, there are no electrical connections between the external conductive contacts 140 and first die 104. That is, in an embodiment of the present invention, all external connections to first die 104 pass through second die 106. In a specific embodiment, all electrical signals to first die 104, other than power and ground signals, are provided by second die 106.

[0021] In an embodiment of the present invention, substrate 102 includes a first insulating layer 130 as illustrated in FIG. 1A. First die 104 is embedded within first insulating layer 130. That is, active surface 108 and sidewalls 101 of first die are in contact with insulating layer 130. A first routing layer 150 comprising a plurality of conductive traces is disposed on first insulating layer 130. A plurality of conductive vias 160 are in first insulating layer 130 and electrically connect conductive traces of the first routing layer 150 to electrical contacts 116 of first die 104. One or more of conductive traces 151 of first routing layer 150 route signals out from the footprint 105 of first die 104 toward an edge of substrate 102. A second insulating layer 132 is disposed on first insulating layer 130 and on first routing layer 150 as illustrated in FIG. 1A. First routing layer 150 is embedded between first insulating layer 130 and second insulating layer 132. The back surface 114 of second die 106 is disposed on second insulating layer 132. A third insulating layer 134 is disposed on second insulating layer 132 and on and around second die 106 as illustrated in FIG. 1A. Second die 106 is embedded within third insulating layer 134 and fully encapsulated and embedded between second insulating layer 132 and third insulating layer 134.

[0022] A second routing layer 152 comprising a plurality of conductive traces is disposed on third insulating layer 134. In an embodiment of the present invention, one or more conductive traces 153 of second routing layer 152 route signals from the edge of substrate 102 to within the footprint 107 of second die 106 to provide electrical connection to second die 106. A plurality of conductive vias 162 are formed in third insulating layer 134 between conductive traces of second routing layer 152 and electrical contacts 118 of second die 106 to electrically connect traces of second routing layer 152 to electrical contacts on second die 118. Additionally, a plurality of conductive vias 164 are formed through second insulating layer

132 and third insulating layer **134** to electrically connect traces of second routing layer **152** to traces of first routing layer **150** as illustrated in FIG. 1A.

[0023] In an embodiment of the present invention, conductive vias **164** have a diameter larger than conductive vias **162**. It is to be appreciated that conductive vias **164** extend deeper into the substrate than do conductive vias **162**. In an embodiment of the present invention, vias **164** have a diameter of between 100-150 μm whereas vias **162** have a diameter of between 30-50 μm . Accordingly, by increasing the diameter of conductive vias **164** the aspect ratio (height:width) of conductive vias **164** is reduced enabling the reliable filling of the conductive vias. It is to be appreciated that although via **164** is shown as being completely filled with a conductive film, via **164** may be formed in such a manner that only the sidewalls of via **164** have a conductive film formed therein, and the center remains unfilled. The subsequent formation of an insulating layer may be used to fill the unfilled volume of the via. See for example FIG. 2J.

[0024] A fourth insulating layer **136** is disposed on third insulating layer **134** and on and around traces of second routing layer **152**. In an embodiment of the present invention, only two routing layers **150** and **152** are provided, one routing layer (**150**) to provide conductive traces to route signals out from footprint **105** of first die **104** and one routing layer **152** to provide conductive traces to route signals to within footprint **107** of second die **106**. If routing layer **152** is the final routing layer of the substrate, a plurality of bond pad openings may be formed in fourth insulating layer **136** to define bond pads on traces **153** of second routing layer to which external electrical contacts **140** are subsequently formed.

[0025] If desired, however, additional routing layers, insulating layers and vias may be included depending upon specific routing requirements. For example, a third routing layer **154** comprising a plurality of conductive traces may be disposed on fourth insulating layer **136**. A plurality of conductive vias **166** may be formed through fourth insulating layer **136** to provide electrical connection between conductive traces of second routing layer **152** and conductive traces of third routing layer **154**. A fifth insulating layer **138** may be formed on fourth insulating layer **136** and on and around conductive traces of third routing layer **154**.

[0026] Still further, fourth routing layer **156** may be disposed on fifth insulating layer **138**. If fourth routing layer **156** is the final routing layer it may include a plurality of routing layers/conductive contact pads **157** to which electrical contacts **140** are coupled. Fourth routing layer **156** may also include routing traces **157** to redistribute the location of contact pads. A plurality of vias **168** are formed through fifth insulating layer **138** to electrically couple traces/contact pads of fourth routing layer **156** to traces of the third routing layer **154**. A final sixth insulating layer **139**, such as a solder mask layer, may be formed on fifth insulating layer **138** and on and around fourth routing layer **156**. Openings are formed in solder mask layer **139** to enable external electrical contacts **140** to be attached to the contact pads of routing layer **156**.

[0027] In embodiments of the present invention, package **100** may include a die attach film (DAF) **124**, such as an epoxy based die bonding film (DBF) attached to the back surface **110** of first die **104**. In other embodiments, the die attach film (DAF) **124** is removed to enable access to the back surface **110** of first die **104**. DAF **124** is not considered part of the substrate **102**. Additionally, in embodiments of the present invention, substrate **102** maybe a coreless substrate

because it is formed on a carrier by a build up layer process where the carrier is eventually removed from the substrate **102**. Still further substrate **102** maybe considered a coreless substrate because it does not include a thick core such as a fiber reinforced glass epoxy resin.

[0028] As illustrated in FIG. 1A, substrate **102** includes at least one routing layer **150** that is located between first die **104** and second die **106**. In addition, in an embodiment of the present invention, substrate **102** includes at least one conductive trace, such as conductive trace **151** that has a portion located between the footprint **105** of first die **104** and footprint **107** of second die **106** and a portion which extends outside footprint **107** of second die **106**. Additionally, although only a single routing layer **132** is shown in FIG. 1A as being formed between first die **104** and second die **106**, one of ordinary skill in the art will appreciate that two or more routing layers may be positioned between first die **104** and second die **106**. Additionally, although three routing layers are shown formed between external contacts **140** and second die **106**, it is to be appreciated that this only illustrative of an embodiment of the present invention and that more or less routing layers may be formed between second die **106** and external contacts **140** depending upon the necessary routing requirements.

[0029] In a embodiment of the present invention external conductive contacts **140** are solder balls arranged in array to provide a ball grid array. The external conductive contacts **140**, however, need not necessarily take the form of balls and may have other shapes or structures, such as but not limited to post, bumps, lands and pins. External contacts **140** enable the electrical connection and communication of semiconductor package **100** to a foundation substrate **170**. For example, when semiconductor package **100** is part of a computer or handheld device, such as a smart phone or handheld reader, the foundation substrate **170** is a motherboard. In other embodiments, the foundation substrate **170** may be another semiconductor package so as to produce a package-on-package (POP) device.

[0030] FIG. 1B is illustration of the package substrate **100** shown in FIG. 1A further delineating specific electrical connections which may be included in substrate **102** in accordance with embodiments of the present invention. In an embodiment of the present invention, substrate **102** includes at least one electrical connection **182** which provides a direct electrical connection between first die **104** and second die **106** where the electrical connection **182** is not electrically connected to an external contact **140**. Such connections are useful for signals that are only communicated between the first die **104** and second die **106**. For example, when first die **104** is a memory device and second die **106** is a logic device, signals such as address signals, data signal, write enable signals and read enable signals may be passed between first die **104** and semiconductor die **106** by direct electrical connections such as electrical connection **182**. Additionally, in an embodiment of the present invention, package substrate **102** may include one or more electrical connections **184** which electrically connect both first die **104** and second die **106** to an external conductive contact **140**. In this way, the signal that is provided to the package **100** through electrical contact **140** is provided to both the first die and second die. An example of such a signal may be power and ground signals, such as VCC and VSS. In another embodiment of the present invention, package substrate **102** includes one or more electrical connections **186** which provide a direct electrical connection between

external contacts **140** and second die **106** without the signal being directly provided to first die **104**. For example, when second die **106** is a logic device, such as a microprocessor, instructions may be provided only to second die **106** by a plurality of electrical connections **186**. Additionally, although not shown in FIG. 1B, substrate **102** may provide one or more electrical connections between first die **104** and an external electrical contact **140** to enable signals to be provided directly to first die **104** without being provided to second die **106**. Embodiments of the present invention include a package substrate **102** which may contain all or some of the electrical connections described above, such as electrical connections **182**, **184** and **186**.

[0031] The semiconductor package **100** having a substrate with a plurality of vertically embedded die includes a fully embedded and surrounded second die **106**. As used in this disclosure, “fully embedded and surrounded” means that all surfaces of the second die **106** are in contact with an insulating film of substrate **102**. The semiconductor package **100** also includes a fully embedded first die **104**. As used in this disclosure, “fully embedded” means that active surface **108** and the entire sidewalls of first die **104** are in contact with an insulating film of substrate **102**. However, first die **104** is not “surrounded” since the back surface **110** of first die **104** is not in contact with an insulating film of substrate **102**. Two embodiments of “fully embedded” for first die **104** described herein. In a first embodiment, as shown in FIG. 1A, there is one surface (e.g. back surface **110**) of the first die that protrudes from the global planarity surface of the die side of substrate **102**, e.g. protrudes from surface **109** of substrate **102** depicted in FIG. 1A. In an embodiment, no surface of first die **104** protrudes from the global planarity surface of the die side of substrate **102**, e.g. no protrusion from surface **109** of substrate **102**.

[0032] In contrast to above definitions of “fully embedded and surrounded” and “fully embedded” a “partially embedded” die is a die having an entire surface but only a portion of the sidewalls in contact with an insulating film of a substrate **102**. In further contrast, a “non-embedded” die is a die having at most one surface, and no portion of the sidewalls, in contact with an encapsulating film of a substrate.

[0033] FIGS. 2A-2L illustrates a method of fabricating a semiconductor package having a plurality of die in embedded within a substrate in accordance with embodiments of the present invention. A carrier **201** is provided. Carrier **201** has an etchstop layer **202**. A second layer **206**, such as copper foil, can be etched to create a recess or cavity **205** around a die mounting surface **204**. In an embodiment of the present invention, carrier **201** does not include a second layer **206** so that there is no recess or cavity formed in carrier **201**.

[0034] FIG. 2B illustrates a cross-sectional view during further processing in the fabrication of a package having a plurality die embedded with a substrate in accordance with an embodiment of the present invention. During processing carrier **201** may be mated to an identical structure **201'** in order to build a back-to-back carrier **210** for processing utility. Consequently, processing throughput is effectively doubled. Description of the processing on carriers **201** and **201'** may be referred to by reference numerals of scribed to the processing of carrier **201** but it may be understood that duplicate processing and structures are produced on carrier **201'**. Carrier **210** includes adhesion release layers **212** **212'** and an adhesive binder **214**. A cutting zone **216** is provided at each end of the carrier **210** for separation processing as illustrated further.

The back to back carrier **210** may form part of a larger panel with a plurality of identical regions having the cross-section of back to back carrier **210** to enable bulk processing. In an embodiment, such a panel has approximately 1000 cavities **205** where a die can be placed.

[0035] FIG. 2C is a cross-sectional view of back to back carrier **210** depicted in FIG. 2B after further processing according to an embodiment of the present invention. Back to back carrier **210** has been further processed by placing a first die **222** onto etch-stop layer **204**. First die **222** has an active surface **224** opposite a back surface **226**. Active surface **224** includes a plurality of contact pads **225** for making electrical contact to first die **222**. First die **222** has a first footprint **229**. In an embodiment, the back surface **226** of first die **222** is attached to etchstop layer **202** utilizing an adhesive layer **228**, such as epoxy base material or die bonding film (DBF). In an embodiment of the present invention, the die with the larger footprint of the two die to be embedded within the substrate is the attached first die (i.e. is first die **222**). Attaching the larger die provides a larger surface area contact with carrier **201** which helps prevent warpage and maintain planarity during the build-up process. In an alternative embodiment, the smaller of the two die is the first die. FIG. 2C also illustrates the addition of first die **222'** onto carrier **201'** to produce apparatus **220**.

[0036] FIG. 2D is a cross-sectional view of apparatus **220** after further processing according to an embodiment of the present invention. Apparatus **220** has been processed to receive a first insulating film **232**. In an embodiment of the present invention, first insulating film **232** is formed by laminating an insulating film onto carrier **201** and first die **222**. After the film is laminated onto carrier **210** and first die **222** it is cured at a suitable temperature, such as about 180° C. In an embodiment of the present invention, first insulating film **232** is an Ajinomoto Build-Up Film (ABF). In an embodiment of the present invention, when carrier **201** includes a second layer **206** forming a cavity **205** and an etch-stop layer **202**, first insulating layer **232** is formed in direct contact with the second insulating layer and the etch-stop layer. Insulating layer **232** is formed onto and in direct contact with active surface **224** as well as sidewalls **223** of first die **222**. In this way, die **222** is embedded within insulating layer **232**. In an alternative to laminating, insulating layer **232** may be formed by spinning on and curing an insulating film. Similarly, a first insulating film **232'** may be formed on and around die **222'** to produce apparatus **230** illustrated in FIG. 2D.

[0037] FIG. 2E is an illustration of the apparatus **230** in FIG. 2D after further processing according to an embodiment of the present invention. A plurality of via holes **242** have been formed through first insulating layer **232** to expose electrical contacts **225** of first die **222**. In an embodiment of the present invention, via holes **242** are formed by laser drilling. Laser drilling may be accomplished using a carbon dioxide (CO₂) gas laser beam, an ultraviolet (UV) laser beam, or an excimer laser beam. In an embodiment of the present invention, via openings **242** having a diameter of between 30-50 microns are formed. Laser drilling according to embodiments, allow for higher connection density as compared with prior art drilling process to enable small via sizes and pitches and in this way, leading to improved design and to scalable miniaturization at low cost. Additionally, laser drilling enables high alignment accuracy (e.g 10 to 15 micron) and throughput (around 2000 vias/second) and a wide range of possible via sizes (such as between 30 micron and about 300

microns) and low cost (about 2 cents per 1000 vias). The combination of high alignment accuracy and small via size make possible via pitches as low as 60 microns, these pitches being much less than typically plated through hole pitches of about 400 microns used on packages containing cores. Via openings 242' may be similarly formed in insulating layer 232' to provide apparatus 240 illustrated in FIG. 2E.

[0038] FIG. 2F is an illustration of the apparatus 240 shown in FIG. 2E after further processing in accordance with an embodiment of the present invention. As illustrated in FIG. 2F, via openings 242 are filled with a conductive material, such as copper, to form a plurality of conductive vias 252 which are electrically connected to contact pads 225 of first die 222. Additionally, a first routing layer 254 comprising a plurality of conductive traces 256, such as copper traces, are formed on first insulating layer 232 and in contact with conductive vias 252 as illustrated in FIG. 2F. In an embodiment of the present invention, at least one conductive trace 256 is formed which is electrically coupled to contact 225 and which extends out to footprint 229 of first die 222 towards the edge of the substrate.

[0039] In an embodiment of the present invention, vias 242 are filled to form conductive vias 252 simultaneously with the formation of conductive traces 256 of first routing layer 254 utilizing a semi-additive process (SAP). In a semi-additive process an electroless seed layer, such as an electroless copper seed layer, having a thickness of, for example, less than 1 micron, is formed over the surface of insulating film 232 as well as into via openings 242 and the sidewalls of via openings 242. A photoresist layer is then deposited on the electroless seed layer and exposed to light and developed whereby a resist pattern is formed leaving non-masked regions corresponding to the pattern where conductive traces 256 are desired. Conductive traces 256 and conductive vias 252 are then formed by electrolytic plating, for example, a copper layer, utilizing the electroless copper plating film as a seed layer. Electroplating is continued until vias 252 are completely filled and first conductive traces 256 are formed to a desired thickness, such as between 2-20 microns. The photoresist mask is then removed and a quick touch etch is used to remove the remaining seed layer.

[0040] The above described SAP technique can be used to fill vias and form conductive traces at a temperature less than 100° C. and typically between 50-80° C. The use of a semi-additive approach enables thin conductive traces to be formed with fine line and space features, for example, line and space feature of less than 30 microns. Utilizing a semi-additive process (SAP) to fill vias 252 and form first routing layer 254 allows first die 222 to be electrically connected to the package substrate without the use of high temperature processes, such as thermal compression bonding or surface mount technology using lead free solders, which are typically used to electrically connect a die to a package substrate in other packaging technologies, such as with flip chip bonding and wire bonding. By using a low temperature process, such as a process at less than 100° C., to electrically connect first die 222 to the substrate, the substrate and die are not exposed to high temperatures which can lead to package warpage due to the CTE mismatch between first die 222 and layers of apparatus 240. Similar processing may be used to form conductive vias 252' and routing layer 254' to provide apparatus 250 illustrated in FIG. 2F.

[0041] FIG. 2G illustrates the apparatus 250 of FIG. 2F after further processing according to embodiments of the

present invention. Apparatus 250 has been further processed to include a second insulating layer 261 and a second die 262 having an active surface 264 and an opposite back surface 266. Active surface 264 of second die 262 includes a plurality of electrical contacts 265 for providing electrical connection to second die 262. Second insulating layer 261 is formed over traces 256 of first routing layer 254 and onto first insulating layer 232 as illustrated in FIG. 2F. The back surface 266 of second die 262 is attached to second insulating layer 261.

[0042] In an embodiment of the present invention, the back surface 266 of second die 262 is attached to second insulating layer 261 utilizing the tackiness of second insulating layer 261. For example, in an embodiment of the present invention, an insulating film, such as ABF, is laminated over routing layer 254 and first insulating layer, the insulating film is then only partially cured, at a temperature of, for example, 70° C., in order to maintain the tackiness of the insulating film. Second die 262 is then placed on the partially cured insulating film with the tackiness of the partially cured insulating film securing second die 262. After securing second die 262 the partially cured insulating layer may be fully cured by, for example, heating to a temperature by about 180° C. to form second insulating layer 261. In this way, no adhesive or die attach film is necessary to secure second die 262 to second insulating layer 261. Elimination of a die attach film reduces the step height of the attached second die thereby helping to reduce the topography of second die 262 and enabling subsequent build up layers to be formed more planar.

[0043] In an embodiment, second die 262 is located such that at least a portion of footprint 269 of second die 262 lies within footprint 229 of first die 222. In an embodiment of the present invention, second die 262 has a footprint 269 which is smaller than the footprint 269 of first die 222 and second die 262 is positioned on insulating layer 261 so that the entire footprint 269 of second die 262 lies within the footprint 229 of first die 222 as illustrated in FIG. 2G. In an embodiment of the present invention, second die 262 is a logic device, such as a microprocessor manufactured by Intel Corporation or a digital signal processor.

[0044] Next, a third insulating layer 268 is formed onto second insulating layer 261 and active surface 264 of second die 262 as shown in FIG. 2G. Second die is fully embedded and surrounded by third insulating layer 268 and second insulating layer 261 as shown in FIG. 2G. In an embodiment of the present invention, third insulating layer 268 is formed by laminating an insulating film onto second insulating layer 261 and second die 262 and curing the laminated film as described above. In an embodiment of the present invention, second die 262 is a thin die, such as die having been thinned to a thickness of between 50-150 microns. It is beneficial to provide a thin die 262 so that insulating layer 268 need not be formed too thick in order to fully encapsulate second die 262. In an embodiment, third insulating layer 268 is formed to a thickness of approximately 20-30 microns thicker than the thickness of the second die in order to provide sufficient isolation of the second die from subsequently formed routing layers. It is to be appreciated that if second die 262 is too thick, then third insulating layer 268 must be formed thick making it difficult to construct reliable via connections to conductive traces 256 of first routing layer 254. A second die 262' may be similarly mounted onto a second insulating layer 258' and a third insulating layer 268' formed over second die 262' to produce apparatus 260 illustrated in FIG. 2G.

[0045] FIG. 2H is an illustration of the apparatus 260 of FIG. 2G after further processing in accordance with an embodiment of the present invention. A plurality of via openings 272 have been formed through insulating layer 268 to expose electrical contacts 265 of second die 262 as illustrated in FIG. 2H. In an embodiment, via openings 272 have diameter between 30-50 μm . Additionally, a plurality of via opening 274 have been formed through third insulating layer 268 and second insulating layer 258 to expose portions of conductive traces 256 of first routing layer 254. In an embodiment, via openings 274 have a larger diameter than via openings 272, such as a diameter of between 100-150 microns. In an embodiment via openings 274 have a diameter of at least two times the diameter of via openings 272. It is to be appreciated that in embodiments the diameter of via openings 274 is, at least in part, determined by the combination of the thicknesses of second insulating layer 261 and insulating layer 268 over conductive traces 254 so that via openings 274 are formed with a manufactureable aspect ratio (height: width). In an embodiment of the present invention, via openings 274 have a larger diameter than via openings 272. In an embodiment of the present invention via openings 274 are formed with a diameter so that via openings have an aspect ratio of about 2:1 or less. In an embodiment of the present invention, via openings 272 and 274 are formed utilizing a laser drilling process as set forth above. Via openings 272' and 274' may be formed in insulating layers 268' and 258' in a similar manner to produce the apparatus 270 illustrated in FIG. 2H.

[0046] FIG. 2I is an illustration of apparatus 270 of FIG. 2H after further processing in accordance with an embodiment of the present invention. Via openings 272 are filled with a conductive material, such as copper in order to form conductive vias 282 in contact with contact pads 265 of second die 262. Additionally, via openings 274 are filled with a conductive material, such as copper, to provide a plurality of conductive vias 284 in contact with conductive traces 256 of first routing layer 254.

[0047] Additionally, apparatus 270 has been further processed to include a second routing layer 286 having a plurality of conductive traces 288. Second routing layer 286 is disposed on third insulating layer 268 as shown in FIG. 2H. In an embodiment of the present invention, at least one conductive trace 288 is formed in contact with both conductive via 282 and conductive via 284. In an embodiment of the present invention, a semi-additive process (SAP), such as described above is used to simultaneously fill vias 282 and vias 284 and form routing layer 286.

[0048] In an embodiment of the present invention, the semi-additive process is designed to produce a conductive layer which is thick enough to completely fill small vias 272 to form completely filled conductive vias 282, but which is not thick enough to completely fill large via openings 274. In such a case, the plated film will form conformally on the sidewalls of via 274 forming a "cup" shaped conductive via 284 with an unfilled central portion 285. The use of a semi-additive process enables second die 262 to be electrically coupled to routing layers of the substrate without the use of high temperature solder bonding processes normally used to electrically connect a die to package substrate. Conductive vias 282' and 284' and second routing layers 286 may be similarly formed to produce apparatus 280 illustrated in FIG. 2I.

[0049] FIG. 2J is an illustration of apparatus 280 of FIG. 2I after further processing in accordance with an embodiment. A fourth insulating layer 292 is formed on second routing layer 286 and on third insulating layer 268. In an embodiment of the present invention, fourth insulating layer 292 is formed by laminating an insulating film onto third insulating layer 268 and second routing layer 286. In an embodiment of the present invention, fourth insulating layer 292 protrudes into unfilled central parts 285 of via 284, as shown in FIG. 2J. A fourth insulating layer 292' may be similarly provided to produce the apparatus 290 illustrated in FIG. 2J. If second routing layer 286 is the final routing layer, the fabrication of the substrate may be completed by forming opening insulating layer 292 to define contact areas or pads in routing layer 286 to which external electrical contacts may be formed.

[0050] If, however, additional routing functionality is required, one or more additional routing layers and insulating layer along with interconnecting vias may be formed as described above. For example, apparatus 290 of FIG. 2J may be further processed in accordance with an embodiment of the present invention to form additional routing layers and insulating layers. For example, a third routing layer 295 having a plurality of traces may be formed on fourth insulating layer 292 and a plurality of conductive contacts 296 may be formed between traces of third routing layer 295 and second routing layer 286. Additionally, a fifth insulating layer 296 may be formed over third routing layer 295. A fourth routing layer 297 having a plurality of conductive traces may be formed on fifth insulating layer 296 and a plurality of conductive vias 298 formed through insulating layer 296 to electrically couple traces of fourth routing layer 297 to third routing layer 295 as illustrated in FIG. 2K. If fourth routing layer 297 is the final routing layer, a final insulating layer 299 may be formed on fourth routing layer 297 and on fifth insulating layer 296. A plurality of openings are then formed through final insulating layer 298 to expose portions of conductive traces of fourth routing layer 297 to define contact pads thereon. Similar processing may be provided to apparatus 290 to produce apparatus 294 illustrated in FIG. 2K.

[0051] FIG. 2L is a cross-sectional elevation of apparatus 295 of FIG. 2K after further processing. The back to back apparatus have been drawn apart by removing margin material at the cutting zone 216 (FIG. 2B) as well as adhesion release layers 212 and etch-stop layer 204. A fabricated multi-chip package 400 is illustrated. A plurality of external electrical contacts, such as conductive bumps 410 may be provided for electrical communication with a foundation substrate (FIG. 1A). External electrical contacts 410 are disposed upon contact pads of final routing layer 297.

[0052] Although the present invention has been described with respect to a multi-chip package having a substrate 102 with two embedded die, the substrate may include three or more embedded die, if desired. For example, in an embodiment of the present invention, a multi-chip package 450 having a substrate 460 with three embedded die may be formed by embedding a third die 470 in an additional embedding insulating layer 480 formed above first insulating layer 130 as illustrated in FIG. 4. An additional routing layer 492 having a plurality of conductive traces and an additional insulating layer 490 may be disposed between additional embedding insulating layer 480 and third insulating layer 130 as shown in FIG. 4. A plurality of conductive vias 494 may be formed between electrical contacts of third die 470 and an additional routing layer 492 to electrically connect third die 470 to

substrate **460**. Additionally, a plurality of large conductive vias **496**, one of which is shown in FIG. **4**, may be formed in additional insulating layer **490** and first insulating layer **130** to electrically connect traces of first routing layer **150** to traces of additional routing layer **492**. A plurality of direct electrical connection may be formed between third die **470** and second die **106** using large conductive vias **164** and **496** and routing layers **492**, **150** and **152** and small vias **162** and **494**. Internal electrical connection may be formed in substrate **460** to connect third die **470** to either second die **106** or first die **105** or to both first die **104** and second die **106** as well as to provide electrical connections between third die **470** and external conductive contacts **140**. Additional die, such as a fourth, a fifth and a sixth die, may be similarly embedded, if desired.

[0053] Additionally, in another embodiment of the present invention, a multi-chip package **500** having a substrate **502** with a third embedded die may be formed by positioning a third die **560** in substrate **102** adjacent to first die **104** as illustrated in FIG. **5**. Vias **580** may be included in first insulating layer **130** to provide electrical connection between first routing layer **150** and third die **560** to electrically couple third die **560** to substrate **502**. In this way, third die **560** is embedded in insulating layer **130** along with first die **104** as illustrated in FIG. **5**. First routing layer **150**, vias **160** and vias **580** may be used to provide one or more direct electrical connections **570** between first die **104** and third die **560** as illustrated in FIG. **5**. Additionally, first routing layer **150** and second routing layer **152** and vias **164**, **162** and **580** may be utilized to provide one or more direct electrical connections between second die **106** and third die **560** as illustrated in FIG. **5**.

[0054] Multi-chip packages **450** and **500** can be fabricated in a manner as described with respect to FIGS. **2A-2L**.

[0055] FIG. **3** shows a computer system according to an embodiment of the invention. System **300** includes a processor **310**, a memory device **320**, a memory controller **330**, a graphics controller **340**, an input and output (I/O) controller **350**, a display **352**, a keyboard **354**, a pointing device **356**, and a peripheral device **358**, all of which may be communicatively coupled to each other through a bus **360**, in some embodiments. Processor **310** may be a general purpose processor or an application specific integrated circuit (ASIC). I/O controller **350** may include a communication module for wired or wireless communication. Memory device **320** may be a dynamic random access memory (DRAM) device, a static random access memory (SRAM) device, a flash memory device, or a combination of these memory devices. Thus, in some embodiments, memory device **320** in system **300** does not have to include a DRAM device.

[0056] One or more of the components shown in system **300** may be included in/and or may include one or more integrated circuit packages, such as the package structure **100** of FIG. **1A**, for example. For example, processor **310**, or memory device **320**, or at least a portion of I/O controller **350**, or a combination of these components may be included in an integrated circuit package that includes at least one embodiment of a structure described in the various embodiments.

[0057] These elements perform their conventional functions well known in the art. In particular, memory device **320** may be used in some cases to provide long-term storage for the executable instructions for a method for forming packaged structures in accordance with embodiments of the present invention, and in other embodiments may be used to store on a shorter term basis the executable instructions of a

method for forming package structures in accordance with embodiments of the present invention during execution by processor **310**. In addition, the instructions may be stored, or otherwise associated with, machine accessible mediums communicatively coupled with the system, such as compact disk read only memories (CD-ROMs), digital versatile disks (DVDs), and floppy disks, carrier waves, and/or other propagated signals, for example. In one embodiment, memory device **320** may supply the processor **310** with the executable instructions for execution.

[0058] System **300** may include computers (e.g., desktops, laptops, hand-helds, servers, Web appliances, routers, etc.), wireless communication devices (e.g., cellular phones, cordless phones, pagers, personal digital assistants, etc.), computer-related peripherals (e.g., printers, scanners, monitors, etc.), entertainment devices (e.g., televisions, radios, stereos, tape and compact disc players, video cassette recorders, camcorders, digital cameras, MP3 (Motion Picture Experts Group, Audio Layer 3) players, video games, watches, etc.), and the like.

[0059] Thus, a multi-chip package having a substrate with a plurality of vertically arranged die embedded therein and its method of fabrication have been described.

We claim:

1. A method of forming a multi-chip package comprising:
 - attaching a first die to a carrier;
 - forming a first insulating layer over said first die and said carrier such that said first die is embedded within said first insulating layer;
 - placing a second die above said first insulating layer; and
 - forming a second insulating layer over said second die so that said second die is embedded within said second insulating layer.
2. The method of claim **1** further comprising forming a routing layer between said first die and said second die.
3. The method of claim **1** further comprising forming a third insulating layer between said first insulating layer and said second insulating layer and attaching said second die to said third insulating layer.
4. The method of claim **3** further comprising:
 - after forming said third insulating layer and prior to attaching said first die partially curing said third insulating layer to form a partially cured third insulating layer;
 - attaching said second die to said partially cured third insulating layer; and
 - after attaching said second die fully curing said partially cured third insulating layer.
5. The method of claim **4** further comprising forming a first routing layer between said first insulating layer and said third insulating layer wherein said third routing layer has a first trace in electrical contact with said first die.
6. The method of claim **4** further comprising forming a second routing layer on said second insulating layer, said second insulating layer having a second trace which is in electrical contact with said second die and said first trace.
7. A method of forming a multi-chip package comprising:
 - attaching a first die having an electrical contact to a carrier;
 - forming a first insulating layer over the carrier and said first die;
 - forming a first via opening in said first insulating layer to expose said electrical contact of said first die;
 - filling said first via opening with a conductive material to form a conductive via;

forming a first routing layer comprising a first conductive trace on said second insulating layer and in contact with said first conductive via;

forming a second insulating layer over said first routing layer;

placing a second die having a second electrical contact above said second insulating layer;

disposing a third insulating layer over said second die and above said second insulating layer;

forming a second conductive via opening in said third insulating layer which exposes said contact of said second die and forming a third via opening in said third insulating layer which exposes said trace of said first routing layer;

filling said second via opening and said third via opening with a conductive material to form a second conductive via in contact with said electrical contact of said second die and a third conductive via in electrical contact with said trace of said first routing layer; and

forming a second routing layer comprising a second trace on said third insulating layer, said second trace formed in contact with said second via and said third via.

8. The method of claim 7 wherein said first via, said second via and said third via are formed by laser drilling.

9. The method of claim 7 wherein a semi-additive process is used to simultaneously fill said first via opening and form said first routing layer.

10. The method of claim 7 wherein said semi-additive process (SAP) is used to fill said second via opening, said third via opening and form said second routing layer.

11. The method of claim 7 wherein said first dielectric layer, said second dielectric layer, and said third dielectric layer are formed by laminating a first dielectric, a second dielectric and a third dielectric, respectively.

12. The method of claim 2 wherein the formation of said first conductive via, said second conductive via, said third conductive via, said first routing layer and said second routing layer, are each formed at a temperature less than 100° C.

* * * * *